CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. TC- 5548

Format No: CP/TP/01

TEST REPORT OF FINE AGGREGATE

Date: 05-08-2017

Lab ID	:	**CP 2018-12-11-56**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15
Agency	:	Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73
Customer's Reference	:	ಕಾ.ಅ/ದಾ.ವಿ/ಕಾ.ಟ/ /2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-08-2017
Sample ID No	:	2018-12-11-56 /03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	03-08-2017
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	82	82	8.2	91.8	90-100	90-100	90-100	95-100
3	2.36 mm	133	215	21.5	78.5	60-95	75-100	85-100	95-100
4	1.18 mm	179	394	39.4	60.6	30-70	55-90	75-100	90-100
5	600 micron	186	580	58.0	42.0	15-34	35-59	60-79	80-100
6	300 micron	173	753	75.3	24.7	5-20	8-30	12-40	15-50
7	150 micron	156	909	90.9	9.1	0-10	0-10	0-10	0-15
8	Pan	91	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

M : 9972924526 | Tel : +91 80 23444891 | e : rschari6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. TC- 5548

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP 2018-12-11-56**

Sample ID No : 2018-12-11-56 /03

Date: 05-08-2017

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.24	-
2	Specific Gravity	2.54	-
3	Material finer than 75 micron(%)	6.5	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರ
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಹೊಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP 2018-12-11-56** **Date: 19/08/2017**

Customer : Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.

Address : T. Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15

Agency : Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73

Customer's Reference : ಕಾ.ಆ/ದಾ.ವಿ/ಕಾ.ಆ/ /2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-08-2017

Sample ID No : 2018-12-11-56 /01

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/08/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	12/08/2017	19/08/2017	149.36 X 150.90 X 151.96	22538	8.154	291.0	12.9	12.4
2	PCC	M15	12/08/2017	19/08/2017	150.69 X 151.66 X 151.43	22852	8.220	279.4	12.2	
3	PCC	M15	12/08/2017	19/08/2017	150.35 X 150.13 X 149.71	22572	9.037	273.3	12.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅ
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬೆಂಗಳೂರು

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP 2018-12-11-56**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15
Agency	:	Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73
Customer's Reference	:	ಕಾ.ಆ/ದಾ.ವಿ/ಕಾ.ಆ/ /2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	14-08-2017
Sample ID No	:	2018-12-11-56 /02
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M15 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date: 09/09/2017

Date of test : 09/09/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	12/08/2017	09/09/2017	151.39 X 151.11 X 150.08	22876	8.445	400.9	17.5	17.6
2	PCC	M15	12/08/2017	09/09/2017	151.17 X 150.43 X 149.31	22740	8.958	402.3	17.7	
3	PCC	M15	12/08/2017	09/09/2017	149.89 X 150.34 X 151.62	22535	8.528	394.0	17.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂ
ಟಿ.ದಾಸರಹಳ್ಳಿ ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬೆಂಗಳೂರು
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP 2018-12-11-56** **Date: 12-08-2017**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15
Agency	:	Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73
Customer's Reference	:	ಕಾ.ಅ/ದಾ.ವಿ/ಕಾ.ಟ/ /2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-08-2017
Sample ID No	:	2018-12-11-56 /06
Sample Type /Size	:	Precast Cover Slab
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	08/08/2017

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	165.51	250.48	1.116	21511	80.9	3.8	3.5	4.4
2	Cover Slab-2	165.49	250.52	1.122	21506	82.3	3.8	3.6	4.4
3	Cover Slab-3	165.50	250.51	1.118	21508	81.5	3.8	3.5	4.4

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂ
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP 2018-12-11-56 **Date: 07-08-2017**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP,
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15
Agency	:	Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73
Customer's Reference	:	ಕಾ.ಅ/ದಾ.ವಿ/ಕಾ.ಆ/ /2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-08-2017
Sample ID No	:	2018-12-11-56 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11) 1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	04-08-2017
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.14	–
2	Finess by Air permeablity method (m^2/kg,Min)	285.6	225m^2/kg, Min
3	Density (gm/cc)	3.14	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	250 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂ...
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : **CP 2018-12-11-56**

Date: 01-09-2017

Customer : Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.

Address : T. Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of Embankement and Site Preparation to Indira Canteen in Ward No.15

Agency : Sri. Shrirama Reddy, no. 62, Behind of Widia, Ashok Nagar, Nagasandra, Bangalore - 73

Customer's Reference : ಕಾ.ಅ/ದಾ.ವಿ/ಕಾ.ಆ/ /2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 03-08-2017

Sample ID No : 2018-12-11-56 /01

Sample Type : Birla Super 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 6, Determination of Compressive Strength, Clause 6

Date of test : 04-08-2017

Environmental Conditions during test : Temperature: 26˚C
Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.6N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.2N/mm^2	Not less than 37 N/mm^2
3	28 Days	54.6N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC- 5648

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP 2018-12-11-56**

Date: 05-08-2017

Sample ID No : 2018-12-11-56 /02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.1	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.6	
3	Specific Gravity	2.66	_
4	Bulk Density(Loose) (Kg/l)	1.52	_
5	Bulk Density(Compacted) (Kg/l)	1.57	_
6	Water Absorption(%)	0.28	_
7	Aggregate crushing Value(%)	25.4	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

Scanned by CamScanner